
ARCO
PARQUET
باركيه ألماني
German Laminate



D - 3531



D - 4617



D - 4616



D - 4619



D - 3902



D - 3901



D - 3900



D - 4618




مـقـاوم للـمـاء
WATER RESISTANT



ألمانيـــا
GERMANY



ضـمـان 25 سنـــة
25 YEAR WARRANTY



8 ملم
8 MM



4 طبقات حماية
AC4



يمسح ولا يغسل
UNWASHABLE



مـقـاوم للـخـدش
SCRATCH RESISTANT



مقـاوم للـرطـوبـة
MOISTURTE RESISTANT

ARCO PARQUET



Mellenium Oak Brown

D - 3531

ARCO PARQUET



Summer Oak

D - 3901

ARCO
PARQUET



Welsh Oak Brown

D - 4618

ARCO
PARQUET



Welsh Oak Grey

D - 4619

ARCO PARQUET



Summer Oak Beige

D - 3902

ARCO PARQUET



Welsh Oak Nature

D - 4617

ARCO PARQUET



Advanced Welsh Oak

D - 4616

ARCO PARQUET



Progress Silver

D - 3900

Technical Datasheet

1. Product description
   - 1.1. Format 1380 x 193 x 8 mm
   - 1.2. Packing 8 boards each pack = 2,124 m²
   - 1.3. Technical description
     - Surface: Three-dimensional interlaced melamine resin
     - Decor: Melamine resin, printed decor
     - Core layer: HDF High Density Fiberboard
     - Balance film: Three-dimensional interlaced melamine resin
   - 1.4. Installation: Mechanical locking system, Clic-System – much easier to install, up to 50% quicker to install (against other systems). Floating installation according to the installation description.
   - 1.5. Classification: ISO 10874
     class 23 : heavy domestic use
     class 32 : general commercial use
     according EN 15468
     EN 14041 CE – Mark
   - 1.6. Fire classification: EN 13501
     C fl– s1 (Hardly inflammable ~ B1)
   - 1.7. Emission: E1 lower than 0,05 ppm
   - 1.8. Slip resistance: Technical class DS
   - 1.9. Thermal conductivity: Thermal resistance according to DIN EN 12667 R= 0,063 [(m² * K)/W]

Catwalk

	Characteristic	Requirements	Unit	Testmethod
1.	Sampling			EN 13329
2.	Thickness	8	mm	EN 13329
3.	Level of use	21 - 32		EN 13329
4.	Wear resistance	AC4		EN 13329
5.	Impact resistance	small Ball ≥ 35 mm big Ball ≥ 750 mm		EN 17368d annexe H
6.	Thickness swelling 24h	≤ 18	%	ISO 24336
7.	Resistance to staining	5,g. 1-2 4,g. 3		EN 438-2
8.	Internal bond	> 1,2	N/mm²	EN 319
9.	Surface soundness	> 1,5	N/mm²	EN 311
10.	Locking strength	Fl 0,2 ≥ 1 Fs 0,2 ≥ 2	kN/m	ISO 24334
11.	Surface layer width	± 0,1	mm	EN 13329
12.	Surface layer length	± 0,3	mm	EN 13329
13.	Squareness	max 0,2	mm	EN 13329
14.	Surface layer straigthness	< 0,3	mm/m	EN 13329
15.	Height difference between elements	max 0,15	mm	EN 13329
16.	Openings between elements	max 0,2	mm	EN 13329
17.	Formaldehyd content	<0.05	ppm	EN 717-1

Erstellt (Datum, Unterschrift) QS	Geprüft und Freigegeben (Datum, Unterschrift) 01.07.2023 N. Bublies	